

HYLOGRIP HY5172 / 760 / 5059

Anaerobic Thread Sealant

Description

Hylogrip HY5172 thread sealant was specifically formulated and developed for the sealing and locking of threaded joints and other sealing applications. The products are resistant to heat, corrosion, vibrations, water, gases, oils, hydrocarbons and many other chemicals. The lubricating properties of Hylogrip HY5172 are due to the PTFE content of the products and can considerably ease torque-up of threaded joints.

Physical Properties, Uncured Product

Class of Locking (DIN 30661)	1 (low strength – easy to dismantle)
Composition	Anaerobic Methacrylate PTFE Modified
Colour	White opaque liquid
Viscosity (Viscosity - Brookfield No 6 @ 20rpm) (BS 5350: Part B8)	16000 cps
Specific Gravity (ASTM D4659)	1.19
Max Thread size	M36
Max Gap Fill	0.2mm
Flash Point	> 100°C (>212°F)
Solvent Content	None

Cured Product

Handling Cure Time (Zinc coated steel)	30 – 120 mins
Functional Cure Time (Zinc coated steel)	3 – 6 hours
Full Cure Time (Zinc coated steel)	24 hours
Breakaway Torque (DIN 54454) (M10 Zinc phosphate nuts and bolts)	5 N.m
Prevailing Torque (M10 Zinc phosphate nuts and bolts)	7 N.m
Temperature Range	-55°C to 150°C (-67°F to 302°F)

Instructions for Use

For best results ensure the surfaces to be sealed are clean, dry and free from contamination such as oil or grease. Surfaces may be cleaned using a suitable solvent such as acetone. Sufficient product to fill the threads should be applied before assembly. Any accessible residue can be easily wiped away using acetone.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.10.2018	Page 1 of 2
	Product name	Hylogrip HY5172 / 760 / 5059 Issue 5	

The joint should be left undisturbed for about one hour, after which it can be safely handled. Full joint strength is achieved after twenty-four hours, although under certain circumstances pressure testing may be carried out earlier than this.

When a more rapid cure is required, or when used on non-metallic components, a layer of Hylomar Anaerobic Primer should be applied to one of the surfaces to be bonded, and allowed to dry (which only requires a few minutes), assembly is then as before.

Typical applications

Hylogrip HY5172 thread sealant may be used as a sealing and locking compound on all types of pipe threads. The product is superior to P.T.F.E. tape, which can become detached and cause operating problems in control systems requiring a high level of particulate cleanliness.

Hylogrip HY5172 has proved extremely effective on stainless steel pipe threads, operating successfully where other compounds of this type have failed to perform satisfactorily. This makes them particularly useful in the construction of hydraulic control systems for the offshore industry, where stainless steel pipework and components are widely used and joint integrity is vital.

Because the compound cures within the joint, it not only prevents leakage from within the pipework, but also excludes the surrounding environment from the joint surface. This helps to reduce the likelihood of crevice corrosion taking place, especially where the joint is immersed in sea water.

Handling & Safety Properties

Please see the product safety data sheet.

Packages

Hylogrip HY5172 is available in 50ml (1.69fl.oz) and 250ml (8.45fl.oz) bottles. For full details please contact our Sales department

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.10.2018	Page 2 of 2
	Product name	Hylogrip HY5172 / 760 / 5059 Issue 5	