

### HYLOGLUE 1000

#### Description

Hyloglue 1000 is a high performance cyanoacrylate adhesive. The product is high viscosity and will form a strong bond to a wide range of substrates in seconds.

#### Typical Properties


Liquid Properties	
Composition	Ethyl Cyanoacrylate
Appearance	Clear Liquid
Specific Gravity (25°C/77°F) (ASTM D4659)	1.05
Viscosity (25°C/77°F Cone and Plate)	Approx. 1000cps

Bonding Speed	
Balsa Wood	<2 seconds
Neoprene	<5 seconds
Nitrile Rubber	<5 seconds
ABS	<15 seconds
Steel	<40 seconds

The Bonding Speed is defined as the time taken to develop at least 0.1 N/mm<sup>2</sup> at 25°C (77°F) and 60% RH

Tensile Strength (ATSM D412 [B])		Lap shear strength (ISO 4587)	
Neoprene	10 N/mm <sup>2</sup>	Steel	20 N/mm <sup>2</sup>
Nitrile Rubber	10 N/mm <sup>2</sup>	ABS	8 N/mm <sup>2</sup>
EPDM	5 N/mm <sup>2</sup>	Polycarbonate	8 N/mm <sup>2</sup>

#### Temperature Resistance



The temperature resistance test was carried out by curing the product between 2 steel lap shears. The test pieces were then left at the test temperature for 1 hour. A lap shear strength test was then performed on each sample.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	17.09.2015	Page 1 of 2
	Product name	Hyloglue 1000 Version 2	

### Environmental Resistance

Exposed to the following conditions for 1000 hours at 25°C (77°F).

Condition	Strength Retention
Ethanol	100%
Water	60%
Air	100%
Automotive Fuels	90%

### Instructions for Use

For best results ensure surfaces to be bonded are clean and free from grease. Apply the glue to one of the substrates and bring the two objects together. Apply pressure to the joint, the length of time depending on the material (see the “bonding speed” table for more information). Any excess product can be cleaned using a suitable solvent such as acetone.

### Safety

CAUTION: bonds skin and eyes in seconds – see safety data sheet for more information.

### Storage

Shelf life is 12 months from date of manufacture when stored between 2°C (35.6°F) and 10°C (50°F) in original unopened containers.

### Packaging

Please contact our sales department for details.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	17.09.2015	Page 2 of 2
	Product name	Hyloglue 1000 Version 2	