

### HYLOMAR M AEROSOL

Non-setting gasket/sealing compound

#### Description

Hylomar M Aerosol is primarily for fine coating of traditional gaskets and components. The product has all of the advantages of Hylomar M but is considerably more convenient to apply.

#### Typical Properties

<b>Chemical basis</b>	Polyester urethane
<b>Consistency</b>	
<b>Area covered after drying</b>	Dependant on dwell time and distance from work piece
<b>Approximate Thickness of Residue</b>	
<b>Typical Temperature Range</b>	
<b>Resistant to</b>	Air, turbine and piston engine combustion products, water, glycol/water and methanol/water mixtures, petroleum and synthetic diester lube oils, gasoline and kerosene fluids (both Avtur and Avcat) and some fluorocarbon refrigerants.
<b>Joint face materials</b>	Harmless to all metals
<b>Electrical metallic's</b>	No staining of copper and silver etc. from traces of volatiles at elevated temperature, and therefore suitable for joints and threads in close proximity to switch mechanisms etc.
<b>Flammability</b>	Extremely flammable due to aerosol gases and acetone. After application, compound is not flammable.
<b>EIapse of time between coating and assembly of joint faces</b>	Approximately 5 - 10 minutes. Maximum time indefinite, satisfactory after several weeks.
<b>Stud Loading</b>	Torque to required figure, allow a few minutes for the compound to settle, then re-torque to the required figure.

#### Instructions for use

The surface should be clean dry and free from grease or oil contamination. A uniform film of Hylomar M Aerosol should be sprayed directly onto each surface. If the compound is to be applied directly onto flange surfaces, care should be taken to prevent excess compound entering oilways

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.09.2015	Page 1 of 2
	Product name	Hylomar M Aerosol Issue 3	

or galleries as blockages may result. Allow the solvent to evaporate. Assemble the joint, bolt down and re-tighten after a few minutes. The compound can be removed using Hylomar Cleaner.

### Typical applications

Hylomar M Aerosol is ideal for coating pre-formed gaskets, weather proofing motors and outdoor, high voltage circuit breakers and flanges where large surface areas are involved.

### Handling and Safety Properties

For further information regarding the safe handling of this product, please refer to the Material Safety Data Sheet.

The shelf life of Hylomar M Aerosol is 12 months when stored in the original unopened containers between 5°C and 25°C (41°F and 77°C), in a dry place, out of direct sunlight.

### Packaging

Hylomar M Aerosol is available in a 200 ml (6.76fl.oz) canister. For full details please contact our Sales Department.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.09.2015	Page 2 of 2
	Product name	Hylomar M Aerosol Issue 3	