

HYLOSIL 302 SILICONE SEALANT

Acetoxy curing RTV silicone sealant

Description

Hylosil 302 Silicone Sealant is a Room Temperature Vulcanising (RTV) general purpose silicone sealant. Once applied the compound reacts with atmospheric moisture to form a tough and durable, rubber seal. It has excellent adhesion to metals, glass, ceramics and plastics. The compound has large gap filling properties which makes it ideal for application to non-machined surfaces and even as cast surfaces.

Hylosil 302 Silicone Sealant is resistant to oil, water and lubricants. It will remain flexible to withstand vibration

Typical Properties, Uncured Product

Colour	Black
Consistency	Non-slump paste
Cross Linking System	Acetoxy
Specific Gravity (DIN 53479)	1.03 g/ml
Solids Content	100%
Extrusion Rate 3mm orifice @ 60 psi	78 g/minute
Skin Forming Time at 23°C/50% RH	6 minutes
Cure Rate @ 25°C and 60% RH	3mm per 24 hours

Cured Product

Tensile Strength DIN 53505, S3A	1.9 N/mm²
Elongation @ Break DIN 53504, S3A	460%
E Modulus @ 100% Elongation DIN 53504, S3A	0.4 N/mm²
Hardness Shore A DIN 53505	22°
Tear Strength ASTM D 624, Form B	5 N/mm²
Shrinkage DIN 53504, S3A	3%
Typical temperature Range	-40° to 240°C (constant operation)
Ignition Temperature DIN 51794	460°C

Instructions for use

Surface should be clean, dry and free from contamination such as oil or grease. Once applied in Gasket applications, the joint should be assembled without delay.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	08.06.2010	Page 1 of 2
	Product name	Hylosil 302 Silicone Sealant issue 5	

Care should be taken when applying the compound to ensure any excess product will not foul any internal channels and cause blockages. Any excess uncured product extruded externally can be wiped away with a damp cloth.

When stripping assemblies that have been sealed with Hylosil 302 Silicone Sealant, carefully scrape away as much of the cured product as possible. The remaining compound can be softened and removed using a suitable Silicone Sealant Remover.

Typical Applications

Hylosil 302 Silicone Sealant is a general purpose adhesive and sealant with many applications in building, engineering and the automotive industry. It has excellent adhesion without primer to metals, glass, ceramics and most rigid plastics. The cured compound is resistant to many solvents, oils, water and lubricants.

Handling and Safety Properties

Not classified according to CHIP 3.1 2005.

Risk Phrases: None.

Safety Phrases: S26 and S28.

For further information please refer to the Safety Data Sheet.

Packaging

Hylosil 302 Silicone Sealant is available in 100ml tubes, 300ml cartridges and 17 litre kegs.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	08.06.2010	Page 2 of 2
	Product name	Hylosol 302 Silicone Sealant issue 5	