

### HYLOSIL 101 (Grey)

Amine curing RTV silicone sealant(when compared with Acetoxy based sealants),

#### Description

Hylomar Silicone Sealant 101(Grey) is a non-corrosive, low odour (when compared with Acetoxy based sealants), Room Temperature Vulcanising (RTV) silicone compound. It is a high performance engineering grade which is used in the automotive industry and for general manufacturing. It can also be used for a variety of applications and is particularly suitable for high strength applications.

Hylomar Silicone Sealant 101(Grey) has good resistance to oils and aqueous anti-freeze agents

Unlike general-purpose silicone sealants, Hylomar Silicone Sealant 101(Grey) contains no solvents and does not give off acetic acid during cure.

#### Typical Properties, Uncured Product

<b>Colour</b>	Grey
<b>Consistency</b>	Non- Slump Paste
<b>Cross Linking System</b>	Amine
<b>Specific Gravity (g/ml) DIN 53479</b>	1.16
<b>Extrusion Rate 3mm orifice @ 60 psi</b>	55 g/min
<b>Skin Time (Minutes) @ 55% RH</b>	10
<b>Cure Rate @ 25°C(77°F) and 60% RH</b>	3mm per 24 hours

#### Cured Product

<b>Tensile Strength (N/mm<sup>2</sup>) DIN 53505, S3A.</b>	2.5
<b>Elongation at Break (%) DIN 53504, S3A</b>	350
<b>Modulus at 100% Elongation DIN 53504, S3A.</b>	0.6 N/mm <sup>2</sup>
<b>Hardness (Shore A) DIN 53505</b>	25 <sup>0</sup>
<b>Tear Strength (N/mm<sup>2</sup>)ASTM D 624, Form B</b>	7
<b>Typical Temperature Range</b>	-50 <sup>0</sup> C to 180 <sup>0</sup> C (-58 <sup>0</sup> F to 356 <sup>0</sup> F) unaltered, Usable to 240 <sup>0</sup> C (464 <sup>0</sup> F)

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.10.18	Page 1 of 2
	Product name	Hylomar 101 grey Issue 5	

### Dielectric Properties

<b>Volume Resistivity Ohm.cm DIN 53482</b> determined dry at 23°C (73.4°F) determined wet at 60°C (140°F)	5 (x10 <sup>14</sup> ) 9 (x10 <sup>13</sup> )
<b>Dielectric Strength (kv/mm) DIN 53481</b>	17
<b>Tracking Resistance DIN 53480</b>	KA 3 c
<b>Dielectric Constant (epilson) at room temperature in a frequency range of 50Hz to 5MHz DIN 53483</b>	3.0 - 2.9
<b>Dissipation Factor (tan) at room temperature in a frequency range of 50Hz to 5Mhz (DIN 53483)</b>	0.01 - 0.005

### Instructions for Use

Ensure both surfaces to be bonded are dry and free from contamination such as oil or grease. Apply a bead directly onto one surface. Once applied, the joint should be assembled without delay.

Care should be taken to ensure any excess compound does not extrude internally and foul any internal oil-ways or other channels and cause blockages. Any excess external product can be wiped away with a damp cloth.

### Typical Applications

Due to its good resistance to oils, Hylomar Silicone Sealant 101(Grey) is ideal for use as a flexible gasket or flange sealant, for use in automotive and general engineering applications.

### Handling and Safety

Please see product safety data sheet.

Product should be stored in temperatures between 5°C and 25°C (41°F and 75°F) in dry conditions out of direct sunlight.

### Packaging

Hylomar Silicone Sealant 101(Grey) is available in 300ml (10.14fl.oz) cartridges and 17 litre (574.84fl.oz) pails.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.10.18	Page 2 of 2
	Product name	Hylomar 101 grey Issue 5	